

C36000

Product Datasheet



Free-Machining Brass


Service. Quality. Value.

Outstanding machinability

C36000 offers excellent machinability with low to moderate strength.

Suitable for high-speed machining operations, C36000 is a free-machining brass product is a low-cost copper zinc lead alloy which is the least expensive of brass alloys with moderate strength. C36000 is one of the widely produced brass alloys in the world. With excellent machinability and formability characteristics, the product finds use in numerous engineering applications. C36000 offers good cor-rsion resistance and is readily brazed or soldered.

If you are looking for a low cost and moderate to low strength brass alloy, this product is highly suitable.



Key Features

- Excellent machinability and formability
- Good corrosion resistance
- Low lead percentage
- Free cutting
- Low cost option

Applications

- Machine screw parts
- High volume parts
- Plumbing components
- Fittings and adaptors
- Fluid connectors

Chemical Composition (weight %)

	Cu	Fe	Pb	Zn	
Min	60.0		2.5		
Max	63.0	0.35	3.7	Rem	

Mechanical Properties (typical)

Tensile Strength	Yield Strength	Elongation at break (in 457.2mm)	Shear Modulus
338 - 469 MPa	124 - 310 MPa*	53%	37 GPa

* Yield strength dependent on temper.

We stock C36000 In round, square, flat and hexagonal forms.

UK Service Centres:

Smiths Belfast [02895 908 897](tel:02895908897)
Smiths Biggleswade [01767 604 704](tel:01767604704)
Smiths Birmingham [0121 728 4940](tel:01217284940)
Smiths Bristol [0117 971 2800](tel:01179712800)
Smiths Chelmsford [01245 466 664](tel:01245466664)
Smiths Gateshead [0191 469 5428](tel:01914695428)
Smiths Horsham [01403 261 981](tel:01403261981)

Smiths Leeds [0113 307 5167](tel:01133075167)
Smiths Manchester [0161 794 8650](tel:01617948650)
Smiths Norwich [01603 789 878](tel:01603789878)
Smiths Nottingham [0115 925 4801](tel:01159254801)
Smiths Redruth [01209 315 512](tel:01209315512)
Smiths Verwood [01202 824 347](tel:01202824347)
Main Office [0845 527 3331](tel:08455273331)

Quality & Testing:



www.smithmetal.com info@smithmetal.com

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.