

Titanium

Typical Applications

Components/equipment for architecture, medical engineering, automotive, chemical plant, pharmaceutical, brewing, food, oil & gas, pulp & paper and marine industries.

Product Description

CP (Commercially Pure) Grade 4 is unalloyed titanium providing reasonably high mechanical strength (typical yield strength 559 MPa) combined with good weldability. Compared with CP Grades 2 and 3 the Grade 4 possess lower toughness despite its higher strength. Grade 4 titanium has a density of 4.54 g/cc - less than 60% that of steel.

Corrosion Resistance

This material offers high corrosion resistance in oxidising, neutral and mildly reducing media, including chlorides. The higher level of oxygen in this CP grade increases the susceptibility to stress corrosion cracking.

Material Specifications

- UNS R50700
- ASTM B348 Grade 4
- BS TA 6 to 9
- AMS 4901
- AIR 9182 T-60
- ASTM 265 Grade 4

Fabrication

- Weldability – good
- Specified bend radius for <0.070 in. x thickness – 2.5
- Specified bend radius for >0.070 in. x thickness – 3.0
- Welded bend radius x thickness – 3.0 (min.)

Availability

Bar, strip, sheet, plate, forgings, castings.

Chemical Composition (weight %)

Weight (%)	C	Fe	N	O	H (sheet)	H (bar)	Ti
Min							
Max	0.1	0.5	0.05	0.4	0.015	0.0125	Balance

Mechanical Properties

	Minimum	Typical
UTS, MPa	552	683
0.2% PS, MPa	483	559
Elongation on 2 in., %	15	23
Reduction of area, %	30	-
Elastic modulus, GPa	-	104
Charpy, V notch impact, J	14	-
Hardness, HV	-	250

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

UK Service Centres:

Smiths Belfast **02895 908 897**
 Smiths Biggleswade **01767 604 704**
 Smiths Birmingham **0121 728 4940**
 Smiths Bristol **0117 971 2800**
 Smiths Chelmsford **01245 466 664**
 Smiths Gateshead **0191 469 5428**
 Smiths Horsham **01403 261 981**

Smiths Leeds **0113 307 5167**
 Smiths Manchester **0161 794 8650**
 Smiths Norwich **01603 789 878**
 Smiths Nottingham **0115 925 4801**
 Smiths Redruth **01209 315 512**
 Smiths Verwood **01202 824 347**
 Main Office **0845 527 3331**

Quality & Testing:



www.smithmetal.com info@smithmetal.com